



**Serbian Ceramic Society Conference**  
**ADVANCED CERAMICS AND APPLICATION X**  
**New Frontiers in Multifunctional Material Science and Processing**

**Serbian Ceramic Society**  
**Institute of Technical Sciences of SASA**  
**Institute for Testing of Materials**  
**Institute of Chemistry Technology and Metallurgy**  
**Institute for Technology of Nuclear and Other Raw Mineral Materials**

**PROGRAM AND THE BOOK OF ABSTRACTS**

**Serbian Academy of Sciences and Arts, Knez Mihailova 35**  
**Serbia, Belgrade, 26-27. September 2022.**

**Serbian Ceramic Society Conference**  
**ADVANCED CERAMICS AND APPLICATION X**  
**New Frontiers in Multifunctional Material Science and Processing**

**Serbian Ceramic Society**  
**Institute of Technical Sciences of SASA**  
**Institute for Testing of Materials**  
**Institute of Chemistry Technology and Metallurgy**  
**Institute for Technology of Nuclear and Other Raw Mineral Materials**  
**PROGRAM AND THE BOOK OF ABSTRACTS**

**Serbian Academy of Sciences and Arts, Knez Mihailova 35**  
**Serbia, Belgrade, 26-27<sup>th</sup> September 2022.**

**Book title:** Serbian Ceramic Society Conference - ADVANCED CERAMICS AND APPLICATION X Program and the Book of Abstracts

**Publisher:**

Serbian Ceramic Society

**Editors:**

Dr. Nina Obradović

Dr. Lidija Mančić

**Technical Editors:**

Dr. Suzana Filipović

Dr. Adriana Peleš Tadić

Dr. Jelena Živojinović

**Printing:**

Serbian Ceramic Society, Belgrade, 2022.

**Edition:**

120 copies

CIP - Каталогизacija y yблuкaцuи  
HapoдHa бuблuоTeкa Cpбиje, Beoгpaд

666.3/.7(048)

66.017/.018(048)

SRPSKO keramičko društvo. Conference Advanced Ceramics and Application : New Frontiers in Multifunctional Material Science and Processing (10 ; 2022 ; Beograd)

Program ; and the Book of abstracts / Serbian Ceramic Society Conference Advanced Ceramics and Application X New Frontiers in Multifunctional Material Science and Processing, Serbia, Belgrade, 26-27. September 2022. ; [editors Nina Obradović, Lidija Mančić]. - Belgrade : Serbian Ceramic Society, 2022 (Belgrade : Serbian Ceramic Society). - 96 str. : ilustr. ; 30 cm

Tiraž 120.

ISBN 978-86-915627-9-3

a) Kepamuka -- Aпcтpaкти б) Hayкa o мaтepиjалимa -- Aпcтpaкти в) Hанoмaтepиjали -- Aпcтpaкти

COBISS.SR-ID 74827529

## P21

### Deviation measurement of SLS PA material regarding location and orientation of printing

Ivana Jevtić<sup>1</sup>, Goran Mladenović<sup>2</sup>, Miloš Milošević<sup>1</sup>, Aleksa Milovanović<sup>1</sup>, Isaak Trajković<sup>1</sup>,  
Milan Travica<sup>1</sup>

<sup>1</sup>Innovation Centre of The Faculty of Mechanical Engineering, University of Belgrade, Kraljice Marije 16 street, Belgrade 11120, Serbia

<sup>2</sup>Faculty of Mechanical Engineering, University of Belgrade, Kraljice Marije 16 street, Belgrade 11120, Serbia

SLS technology is widely used in several industries worldwide mainly due to its ability to manufacture complex geometry components with less effort compared to conventional methods. Such technology uses materials in powder form, the most common ones are polyamides (PA), polystyrenes, thermoplastic elastomers, and polyaryletherketones. Research covers flexural PA12 specimens, with CAD model dimensions selected according to the ISO 178 standard, with 96x8x4 [mm] in bulk. Printing was performed on Fuse 1 (FormLabs, Summerville, MA) machine with four batches, differing in printing orientation and printing location. Vertical and horizontal orientations are applied, and each orientation is combined with the printing location, i.e., in the middle and on the edge of the powder bed. Printed specimens are scanned and obtained scans are then compared with original CAD model in the GOM Inspect program. All four specimen batches have deviation maximum on lateral sides, where the surface is minimal. Nearly 0.42 mm deviations are present in horizontally printed specimens placed in the middle of the powder bed, and these values are maximal recorded deviations. Worth mentioning are vertical specimens printed in the middle, which show not only lateral deviations but possess 0.07 mm deviations on largest surface, i.e., on 96x8 mm one.

## P22

### Optically active SrGd<sub>2</sub>O<sub>4</sub> phase: Yb<sup>3+</sup>/Ho<sup>3+</sup> and Yb<sup>3+</sup>/Tm<sup>3+</sup> co-doping

Tijana Stamenković<sup>1</sup>, Vesna Lojpur<sup>1</sup>, Nadežda Radmilović, Marina Vuković<sup>2</sup>,  
Ivana Dinić<sup>3</sup>, Lidija Mančić<sup>3</sup>

<sup>1</sup>Department of Atomic Physics, Vinča Institute of Nuclear Sciences, National Institute of the Republic of Serbia, University of Belgrade, Serbia

<sup>2</sup>Innovative Centre, Faculty of Chemistry, University of Belgrade, Serbia

<sup>3</sup>Institute of Technical Sciences of SASA, Belgrade, Serbia

Optically active materials have a wide range of applications. The phenomenon of light conversion includes two main types: up-conversion, which is the ability of conversion lower energy photons into the ones with the higher energy, and down-conversion, which is vice versa. Orthorhombic SrGd<sub>2</sub>O<sub>4</sub> doped with rare earth elements is established to have promising optical characteristics, but rarely explored until nowadays as up-converting material. Due to the phonon energy of around 475 cm<sup>-1</sup>, which is lower than in many other compounds commonly used hosts, this one has a great perspective as an optically active

material. Here, for the first time two combinations of rare earth dopant ions,  $\text{Yb}^{3+}/\text{Ho}^{3+}$  and  $\text{Yb}^{3+}/\text{Tm}^{3+}$ , with different mutual ratios were chosen as pairs for inducing up-conversion. Sol-gel assisted combustion synthesis, which comprises citric acid as chelator and glycine as fuel, was used to obtain powdered samples that are subsequently thermally treated for 3.5 h at  $1100^\circ\text{C}$ . X-ray powder diffraction analysis (XRPD) was performed to determine crystal structure. Morphology characteristics were observed by scanning and transmission electron microscopy (SEM/TEM). Photoluminescent up-converting properties were measured in function of laser power (976 nm) in order to define optimal doping concentration and up-conversion mechanism.

### P23

#### Related effects of $\text{Ca}_{1-x}\text{Gd}_x\text{MnO}_3$ ( $x = 0.05, 0.1, 0.15, 0.2$ ) compound

Milena Rosić<sup>1</sup>, Maria Čebela<sup>1</sup>, Jelena Gulicovski<sup>1</sup>, Vladimir Dodevski<sup>1</sup>, Sanja Krstić<sup>1</sup>,  
Milan Kragović<sup>1</sup>

<sup>1</sup>Laboratory for Material Science, Institute of Nuclear Sciences „Vinča“, National Institute of the Republic of Serbia, University of Belgrade, PO Box 522, 11001 Belgrade, Serbia

We have used theoretical and experimental methods to investigate the octahedral tilting and related effects of  $\text{Ca}_{1-x}\text{Gd}_x\text{MnO}_3$  ( $x=0.05, 0.1, 0.15, 0.2$ ) compound. Both methods have shown that orthorhombic-perovskite structure (space group  $Pnma$ ) is the most stable form and according to Glazer's classification belongs to  $a^-b^+a^-$  tilt system. Our bond valence calculations (BVC) have shown ten additional perovskite-related modifications of the equilibrium  $\text{Ca}_{1-x}\text{Gd}_x\text{MnO}_3$  structure, and their stability has been investigated as function of Gd doping. We have further studied the influence of gadolinium amount on Mn-O bond angles and distances, tilting of  $\text{MnO}_6$  octahedra around all three axes and deformation due to the presence of Jahn-Teller distortion around  $\text{Mn}^{3+}$  cation, and calculated the amount of  $\text{Mn}^{3+}$  in the system. The infrared reflection spectra of  $\text{Ca}_{1-x}\text{Gd}_x\text{MnO}_3$  samples confirmed XRD results that  $\text{Ca}_{1-x}\text{Gd}_x\text{MnO}_3$  nanopowders are of  $Pnma-1$  structure and that the tilting of octahedra are increased with Gd doping. The EPR spectra are in accordance with the assumption that EPR linewidth is Mn-O-Mn angle dependent. The studied samples showed that small octahedra tilting in these samples brought only a small change of the EPR linewidth.