

THIRTEENTH ANNUAL CONFERENCE

YUCOMAT 2011

Hunguest Hotel Sun Resort Herceg Novi, Montenegro,
September 5-9, 2011
<http://www.mrs-serbia.org.rs>

Programme and The Book of Abstracts

Organised by:
Materials Research Society of Serbia

under the auspices of
Federation of European Material Societies
and
Materials Research Society

Title: THE THIRTEENTH ANNUAL CONFERENCE
YUCOMAT 2011
Programme and The Book of Abstracts

Publisher: Materials Research Society of Serbia
Knez Mihailova 35/IV, 11000 Belgrade, Serbia
Phone: +381 11 2185-437; Fax: + 381 11 2185-263
<http://www.mrs-serbia.org.rs>

Editor: Prof. Dr. Dragan P. Uskoković

Technical editor: Aleksandra Stojičić

Cover page: Aleksandra Stojičić and Milica Ševkušić

Copyright © 2011 Materials Research Society of Serbia

Acknowledgment:



Printed in: Biro Konto
Sutorina bb, Igalo – Herceg Novi, Montenegro
Phones: +382-31-670123, 670025, E-mail: bkonto@t-com.me
Circulation: 250 copies. The end of printing: August 2011

P.S.B.46.

CHARACTERIZATION SOLID, VISCOELASTIC AND LIQUID MATERIALS BY OPTO-MAGNETIC SPECTROSCOPY

B. Jeftić, I. Hut, D. Mladenović, J. Munćan, Z. Golubović, D. Šarac, A. Tomić
*NanoLab, Biomedical Engineering, Faculty of Mechanical Engineering,
University of Belgrade, Serbia*

Optomagnetni fingerprint (OMF) is a new method of surface material investigation, which is based on light-matter interaction. Valence electrons and their electrical and magnetic forces are starting point of departure. Light-matter interaction will be different depending of covalent bonds, ion-ion, ion-dipol, dipol-dipol interactions presence in material surface (thin layer).

In order to investigate different types of materials we have investigated the solid materials (metal), viscoelastic matter (skin) and liquid (water). For each sample we took 300 digital images under the influence of white light and the white light under the Brewster angle. Using spectral convolution algorithm we made intensity-wavelength difference diagrams. Analyzing them it has been shown that average value (AV) and standard deviation (SD) are different for those three material types'. AV and SD are more compact for metal, water and skin, respectively.

P.S.B.47.

RIETVELD REFINEMENT OF BARIUM TITANATE STANNATE CRYSTAL STRUCTURE

Lj. Veselinović¹, M. Mitrić², M. Vukomanović¹, S. Marković¹, D. Uskoković¹
¹*Institute of Technical Sciences of SASA, Belgrade, Serbia*
²*The Vinča Institute of Nuclear Sciences, Belgrade, Serbia*

The barium titanates have wide application in electronic industry as a dielectric and ferroelectric materials. The BaTiO₃ doped with Sn is important for practical application in ceramic capacitors as well as in functionally graded materials. It is known that BaTiO₃ materials have the typical perovskite crystal structural. Their ideal crystal structure is a centrosimetric cubic structure with $Pm\bar{3}m$ space group. However, the changes in temperature, pressure, and composition lead to phase transitions and crystal structure transformations.

In this study using by Rietveld refinement, we resolved crystal structure of barium titanate stannate (BTS) BaTi_{1-x}Sn_xO₃ ($x = 0, 0.025, 0.05, 0.07, 0.10, 0.12, 0.15$ and 0.20) solid solutions. The powders were prepared by simple solid state reaction at 1420 °C, in air for 2 hours. The structural investigations of the BTS samples were done at room temperature using an X-ray diffraction, Raman spectroscopy and TEM micrograph. The Rietveld refinement of the X-ray diffraction data was used to analyze the structural changes depending on amount of the Sn⁴⁺ ions in the BTS. Obtained data show that increasing of Sn amount in the structure provokes the transformation of crystal structure from tetragonal to cubic one. We suppose that the absence of orthorhombic and rhombohedral phases is probably a consequence of phase ($0.025 \leq x < 0.20$) stabilization caused by method of sample preparation (high temperature solid state reaction).